

Technical Data Sheet

Quality Specification

Palm Diamond 68 H

	Basis Weight	Bulk	Brightness	Breaking Length (MD)	Opacity	Roughness TS/BS PPS 1.0 Mpa	Gloss Hunter (75°)
Dimension	[g/m ²]	[cm ³ /g]	[%]	[m]	[%]	[μm]	[%]
Standard	ISO 536	ISO 534	ISO 2470	ISO 1924	ISO 2471	ISO 8791-4	ISO 8254-1
	48.8	1.0	68	5,800	95.0	2.0	28
	52.0	1.0	68	5,800	96.0	2.0	28
	56.0	1.0	68	5,800	96.0	2.0	28

Colour Specification: **Standard** ISO 5631 L* (C/2°) 85.0
a* (C/2°) -0.3
b* (C/2°) 2.0

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Tolerance: The tolerances are within the industrial standard range.

Certificates: ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC, Blue Angel, EU Ecolabel
(Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.)

PrePress Guidelines: ICC Paper Profile: PSO_INP_Paper_eci.icc
Characterisation data: FOGRA48L.txt

Issue date 1 January 2021

Technical Data Sheet

Quality Specification

Palm Diamond 68 G

	Basis Weight	Bulk	Brightness	Breaking Length (MD)	Opacity	Roughness (TS/BS) PPS 1.0 MPa	Gloss Hunter (75°)
Dimension	[g/m ²]	[cm ³ /g]	[%]	[m]	[%]	[μm]	[%]
Standard	ISO 536	ISO 534	ISO 2470	ISO 1924	ISO 2471	ISO 8791-4	ISO 8254-1
	48.8	1.0	68	5,800	95.0	2.0	28
	52.0	1.0	68	5,800	96.0	2.0	28
	56.0	1.0	68	5,800	96.0	2.0	28

Colour Specification: **Standard** ISO 5631 L* (C/2°) 85.0
a* (C/2°) -0.3
b* (C/2°) 2.0

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Tolerance: The tolerances are within the industrial standard range.

Certificates: ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC, Blue Angel, EU Ecolabel
(Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.)

PrePress Guidelines: ICC Paper Profile: PSRgravureMF.icc
Characterisation data: PSRgravureMF_ECI2002.txt

Issue date 1 January 2021