



# Technical Data Sheet

## Quality Specification

### Palm Top 68 H

	Basis Weight	Bulk	Brightness	Breaking Length (MD)	Opacity	Roughness (TS/BS) Bendtsen	Gloss Hunter (75°)
Dimension	[g/m <sup>2</sup> ]	[cm <sup>3</sup> /g]	[%]	[m]	[%]	[ml/min]	[%]
Standard	ISO 536	ISO 534	ISO 2470	ISO 1924	ISO 2471	ISO 8791-2	ISO 8254-1
	45.0	1.2	68	5,500	94.0	40	22
	48.8	1.2	68	5,500	95.0	40	22
	52.0	1.2	68	5,500	96.0	40	22

<b>Colour Specification:</b>	<b>Standard</b> ISO 5631	L* (C/2°) 85.0 a* (C/2°) 0.0 b* (C/2°) 3.5
<b>Preconditioning:</b>	ISO 187, 23°C, 50% relative humidity	
<b>Tolerance:</b>	The tolerances are within the industrial standard range.	
<b>Certificates:</b>	ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC, Blue Angel, EU Ecolabel (Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.)	
<b>PrePress Guidelines:</b>	ICC Paper Profile: PSO_INP_Paper_eci.icc Characterisation data: FOGRA48L.txt	

Issue date 01.01.2021

[www.palm.de](http://www.palm.de)



# Technical Data Sheet

## Quality Specification

### Palm Top 60 H

	Basis Weight	Bulk	Brightness	Breaking Length (MD)	Opacity	Roughness (TS/BS) Bendtsen
Dimension	[g/m <sup>2</sup> ]	[cm <sup>3</sup> /g]	[%]	[m]	[%]	[ml/min]
Standard	ISO 536	ISO 534	ISO 2470	ISO 1924	ISO 2471	ISO 8791-2
	40.0	1.2	60	5,500	92.0	40
	42.5	1.2	60	5,500	93.0	40
	45.0	1.2	60	5,500	94.0	40
	48.8	1.2	60	5,500	95.0	40

<b>Colour Specification:</b>	<b>Standard</b> ISO 5631	L* (C/2°) 83.1 a* (C/2°) 0.0 b* (C/2°) 3.5
<b>Preconditioning:</b>	ISO 187, 23°C, 50% relative humidity	
<b>Tolerance:</b>	The tolerances are within the industrial standard range.	
<b>Certificates:</b>	ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC, Blue Angel, EU Ecolabel (Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.)	
<b>PrePress Guidelines:</b>	ICC Paper Profile: PSO_INP_Paper_eci.icc Characterisation data: FOGRA48L.txt	

Issue date 01.01.2021

[www.palm.de](http://www.palm.de)