



Cartiere SACI S.p.a.

SCHEDA TECNICA – PAPIER SPEZIFIKATION - PAPER SPECIFICATIONS – FICHE TECHNIQUE

Type Paper

EcoTech

Grammatura <i>Substance - Flächengewicht - Grammage</i>	gr/mq	<i>Metodo prova ISO</i>	130	140
Carico di rottura M.D. <i>Tensile Strength - Laufrichtung Bruchlast - Charge de rupture</i>	KN/m	<i>1924/3</i>	6,63	7,14
Carico di rottura C.D. <i>Tensile Strength - Laufrichtung Bruchlast - Charge de rupture</i>	KN/m	<i>1924/3</i>	3,06	3,29
Allungamento M.D. <i>Elongation - Laufrichtung Streckung - Allongment</i>	%	<i>1924/3</i>	1,5	1,5
Allungamento C.D. <i>Elongation - Laufrichtung Streckung - Allongment</i>	%	<i>1924/3</i>	3,3	3,3
Lunghezza di rottura M.D. <i>Breaking length - Laufrichtung reißlänge - Longueur de rupture</i>	m	<i>1924/3</i>	5200	5200
Lunghezza di rottura C.D. <i>Breaking length - Laufrichtung reißlänge - Longueur de rupture</i>	m	<i>1924/3</i>	2400	2400
Media <i>Lenght - Querrichtung - Moyenne</i>	m	-	3800	3800
Indice lacerazione M.D. <i>Tear index - Durchreißung - Indice de déchirement</i>	mNm/g	<i>1974</i>	5	5
Indice lacerazione C.D. <i>Tear index - Durchreißung - Indice de déchirement</i>	mNm/g	<i>1974</i>	6	6
Porosità Gurley MF <i>Porosità gurley - Porositat Gurley - Porosità Gurley</i>	sec	<i>5636/5</i>	50 < x < 60	55 < x < 65
Porosità Gurley C <i>Porosità gurley - Porositat Gurley - Porosità Gurley</i>	sec	<i>5636/5</i>	40 < x < 50	55 < x < 65
Cobb 60"	gr/mq	<i>535</i>	35	35
Resistenza allo scoppio <i>Bursting Strength - bersten - Resistance d'eclatement</i>	KPa	<i>2758</i>	230	240
Bendsten Test Top <i>Con calandra - With Calander</i>	ml/min	<i>8791-2</i>	420 < x < 480	420 < x < 480
Bendsten Test Bottom <i>Con calandra - With Calander</i>	ml/min	<i>8791-2</i>	970 < x < 1030	1070 < x < 1130
Resistenza Residua (se richiesto) <i>Treatment Wet Strength (if requested)</i>	%	<i>1924/3</i>	15 < x < 20	15 < x < 20

I valori riportati in tabella sono garantiti con un intervallo del +/- 5%
The values, reported on the table, are guaranteed in a range of +/- 5%
Die angegebenen Werte unterliegen einer Toleranz von +/- 5%

Tabella aggiornata il 03 Gennaio 2022



Paper made in Italy

www.interface-nrm.co.uk

