



Cartiere SACI S.p.a.

SCHEDA TECNICA – PAPIER SPEZIFIKATION - PAPER SPECIFICATIONS – FICHE TECHNIQUE

Type Paper

KTech

Grammatura <i>Substance - Flächengewicht - Grammage</i>	gr/mq	<i>Metodo prova ISO</i>	120	130	140	170
Carico di rottura M.D. <i>Tensile Strength - Laufriichtung Bruchlast - Charge de rupture</i>	KN/m	1924/3	7,53	8,16	8,79	10,7
Carico di rottura C.D. <i>Tensile Strength - Laufriichtung Bruchlast - Charge de rupture</i>	KN/m	1924/3	3,29	3,57	3,84	4,67
Allungamento M.D. <i>Elongation - Laufriichtung Streckung - Allongment</i>	%	1924/3	1,9	1,9	1,9	1,9
Allungamento C.D. <i>Elongation - Laufriichtung Streckung - Allongment</i>	%	1924/3	3,6	3,6	3,6	3,6
Lunghezza di rottura M.D. <i>Breaking length - Laufriichtung reilnge - Longueur de rupture</i>	m	1924/3	6400	6400	6400	6400
Lunghezza di rottura C.D. <i>Breaking length - Laufriichtung reilnge - Longueur de rupture</i>	m	1924/3	2800	2800	2800	2800
Media <i>Length - Querrichtung - Moyenne</i>	m	-	4600	4600	4600	4600
Indice lacerazione M.D. <i>Tear index - Durchreiung - Indice de dchirement</i>	mNm/g	1974	7	7	7	7
Indice lacerazione C.D. <i>Tear index - Durchreiung - Indice de dchirement</i>	mNm/g	1974	8	8	8	8
Porosit Gurley MF <i>Porosit gurley - Porosit Gurley - Porosit Gurley</i>	sec	5636/5	45 < x < 55	45 < x < 55	45 < x < 55	45 < x < 55
Porosit Gurley C <i>Porosit gurley - Porosit Gurley - Porosit Gurley</i>	sec	5636/5	55 < x < 65	55 < x < 65	55 < x < 65	55 < x < 65
Cobb 60"	gr/mq	535	35	36	38	38
Resistenza allo scoppio <i>Bursting Strength - bersten - Resistance d'clatement</i>	KPa	2758	300	360	360	380
Bendsten Test Top <i>Con calandra - With Calander</i>	ml/min	8791-2	470 < x < 530	470 < x < 530	570 < x < 630	1370 < x < 1430
Bendsten Test Bottom <i>Con calandra - With Calander</i>	ml/min	8791-2	870 < x < 930	870 < x < 930	1070 < x < 1130	1970 < x < 2030
Resistenza Residua (se richiesto) <i>Trattment Wet Strength (if requested)</i>	%	1924/3	20 < x < 25	20 < x < 25	20 < x < 25	20 < x < 25

I valori riportati in tabella sono garantiti con un intervallo del +/- 5%
The values, reported on the table, are guaranteed in a range of +/- 5%
Die angegebenen Werte unterliegen einer Toleranz von +/- 5 %

Tabella aggiornata il 03 Gennaio 2022



Paper made in Italy

www.interface-nrm.co.uk

