




SCHÖNOX® ZM

Very low emission, self levelling, cementitious smoothing and levelling compound

for all substrates suitable for laying, also for improvement areas interior. SCHÖNOX ZM is characterised by a very low shrinkage and good self levelling properties.



Product characteristics

- EMI CODE EC 1^{PLUS}: very low emission
- RAL UZ 113: Environment-friendly, because very low-emission
- Meets the requirements of the Marine Equipment Directive (MED) 2014/90/EU
- for interior use
- self-levelling
- very smooth application
- very good grindable
- optimized absorptivity
- high level of hardness and strength
- suitable for application on subfloor heating systems
- ideal in combination with Sika coatings
- synthetic resin-modified
- layer-thickness 1,0 to 15 mm without aggregates
- layer-thickness 10 to 25 mm with aggregates
- drying by hydration
- pumpable
- low tension/stress
- suitable for castor wheels loading with layer-thickness more than 1,0 mm according to EN 12 529
- low porosity surface
- high filling capacity in deepenings
- low in chromate according to REACH

Applications

SCHÖNOX ZM is suitable for filling, smoothing, evening and levelling of substrates:

- under textile and elastic coverings
- for full-surface levelling under parquet, layer thickness at least 2,0 mm in interior areas.
- for full-surface levelling under sealings and coatings (Note the system design in combination with Sika coatings)

Substrates

SCHÖNOX ZM is suitable for filling, smoothing, evening and levelling of:

- concrete
- cement and rapid cement screeds
- calcium sulphate based screeds
- old substrates with old water-resistant adhesive residues
- mastic asphalt screeds (sanded) AS IC 10 and AS IC 15 according to EN 13 813, layer-thickness 1,5 to 3,0 mm
- Old mastic asphalt screeds AS IC 10 and AS IC 15 (if necessary, obtain advice on the hardness class test in an asphalt laboratory) according to EN 13 813, often contain cracks or are embrittled, depending on their composition, age, strength and use. This renovation substrate does not display sufficient load-bearing strength for taking even a low-stress, cementitious levelling compounds. For this purpose, we recommend using stress-free, gypsum SCHÖNOX-levelling compound. If in doubt, please obtain supplementary information.
- magnesia screeds with mineral aggregates
- old substrates such as ceramic tiles, natural stones and terrazzo
- suitable particle board or OSB constructions, screwed

Requirements of substrate

- Adequate strength, load bearing capacity, dimensional stability and permanent dryness.
- Free of residues which reduce adhesion, e.g. dust, dirt, oil, fat and loose particles.
- Surface treatments or any "friable" areas of the subfloor must be mechanically removed and the subfloor repaired with SCHÖNOX levelling compounds as required.
- Old, loose and weak levelling layers should be removed mechanically.
- With subsequent installation of floor coverings, cement screeds are required to display a residual moisture reading of ≤ 2.0 CM-% (heating screeds \leq

Technical data

- Pot life: approx. 30 minutes at 20 °C
- Ready for foot traffic: after approx. 2 hours
- Ready for covering:
 - up to 3 mm after approx. 12 hours for all kinds of coverings
 - up to 5 mm after approx. 24 hours for all kinds of coverings
 - up to 10 mm after approx. 48 hours for all kinds of coverings
- Application temperature: not below 5 °C floor temperature
- Material consumption: approx. 1,5 kg/m²/mm
- Reaction to fire: A1 / A1_{f1}

All values are approximate and are subject to climatic fluctuations.



SCHÖNOX® ZM

1.8 CM-%), calcium sulphate screeds should have a reading of ≤ 0.5 CM-% (heating screeds ≤ 0.3 CM-%).

- Layers of water-soluble adhesives, e.g. sulphite-waste-adhesives, are to be mechanically removed. Remaining adhesive residues should be primed with SCHÖNOX HP RAPID.
- Old water-resistant adhesives are to be mechanically removed as far as possible.
- Old floors, such as ceramic tiles are to be thoroughly cleaned and sanded.
- Rooms in buildings without a basement, are to be sealed against rising dampness in compliance with the standard.
- The requirements of the relevant valid standards, guidelines and data sheets apply.

Priming

- **normal absorbent substrates such as:**
 - cement screeds
 - rapid cement screeds
 - concrete
 prime with SCHÖNOX VD (1:3) or SCHÖNOX KH FIX.
- **non-absorbent, smooth, sound substrates such as:**
 - mastic asphalt screeds, insufficient sanded
 - water-resistant adhesive residues (removed as far as possible)
 - ceramic tiles (thoroughly cleaned and abraded)
 prime with SCHÖNOX SHP or SCHÖNOX VD (neat).
- **calcium sulphate substrates such as:**
 - calcium sulphate screeds
 prime with SCHÖNOX KH FIX (drying time 60 minutes) or SCHÖNOX VD (1:1 / drying time at least 24 hours).
 For layer-thickness exceeding 10 mm we recommend priming with SCHÖNOX HP RAPID.
- **magnesia screeds (not xylolite):**
 prime with SCHÖNOX SHP.
- **Wooden substrates like e.g.:**
 - Chipboard or OSB
 protect against moisture with SCHÖNOX VD (neat)(drying time 2 hours).

Mixing ratio

- For 25,0 kg SCHÖNOX ZM approx. 6,25 - 6,50 l water

Extended levelling compound:

The additive is added last.

Max. 6,50 l water for 25,0 kg SCHÖNOX ZM. The additive is added last.

Layer thickness of 10 to 25 mm:

Bulking material approx. 65 wt.% corresponds to 16,0 kg or 10 l of SCHÖNOX QUARZSAND 0,1 - 3,0 mm for 25,0 kg SCHÖNOX ZM

Recommended method of working

- Using a clean receptacle, add SCHÖNOX ZM to cold clean water to form a homogeneous mixture. Use of a mixer with disc stirring rod is recommended. After a short maturing time, mix again thoroughly. Then pour out the levelling compound and spread using a smoothing trowel. Even surfaces are easily achieved with the SCHÖNOX SCHWEDENRAKEL. With the use of the SCHÖNOX SCHWEDENRAKEL it is possible to achieve an even surface without difficulties. It is usually not necessary to remove trowelling defects or to level more than once.
- In the case of higher layer-thickness, contact with vertical structures should be avoided by putting in a perimeter isolating strip.
- If a second layer of levelling compound is to be applied, the first levelling compound layer should be primed with SCHÖNOX VD (1:1) or SCHÖNOX KH FIX when dry. The maximum layer thickness may not be exceeded in case of two-layer application. The second layer may not exceed the layer thickness of the first.
- Carry out preparatory work - such as filling joints, evening out hollows and unevenness - using the sturdy repair mortar SCHÖNOX RR.
- Protect curing SCHÖNOX ZM levelling layers from high ambient temperatures, direct sunlight and draughts.
- Full-surface levelling is needed under elastic coverings at least 2mm.

- Contact to metal like water-bearing pipes must be avoided (e.g. sealing of pipe penetrations), because especially galvanised steel pipes have no sufficient corrosion protection.
- Clean tools in water immediately after use.

Packaging

- 25.0 kg paper sack
- 1000 kg Big Bag

Storage

- Store SCHÖNOX ZM in cool, dry conditions.
- Storage life of 6 months.
- Opened packages should be closed immediately and used up as soon as possible.

Disposal

- Empty packaging of all trickles and dispose of in accordance with the regulations.
- For the disposal of product residues, waste water and containers with adherent product residues please follow the local governmental regulations.
- Do not empty into drains, waters or soil.

EMICODE

- EC 1^{PLUS}: very low emission

GISCODE

- ZP1 - cement products, low in chromate

EPD - Self-declaration

Sika Deutschland GmbH declares that the product fullfills the criteria for modified mineral mortars of group 1.

ENVIRONMENTAL PRODUCT DECLARATION

acc. to ISO 14025 and EN 15804

Owner of declaration

FEICA - Association of the European Adhesive and Sealant Industry

Editor

Institut für Bauen und Umwelt e.V. (IBU)

Program owner

SCHÖNOX® ZM

Institut für Bauen und Umwelt e.V. (IBU)

Number of declaration

EPD-FEI-20160017-IBG1-EN

Date of issue

23.05.2016

Valid until

22.05.2021

Instructions

- All information applies to standard conditions and relates to the non-extended levelling compound.
- SCHÖNOX ZM contains cement. Alkaline reaction when it comes in contact with moisture, therefore protect skin, eyes and respiratory system. Do not breathe in dust. In case of contact rinse immediately with plenty of water. In case of contact with eyes seek additional medical advice.
- Please follow the relevant product data sheets when using complementary products. If in doubt, we recommend obtaining further information from the manufacturer.
- The BEB-leaflet "Beurteilen und Vorbereiten von Untergründen; Verlegen von elastischen und textilen Bodenbelägen, Schichtstoffelementen (Laminat), Parkett und Holzpflaster; Beheizte und unbeheizte Fußbodenkonstruktionen" should be followed.
- Keep out of the reach of children.
- Insure a good ventilation during application and drying.
- Avoid eating, drinking and smoking while working with the product.
- In case of contact with eyes or skin, rinse immediately with plenty of water.
- Wear suitable protective gloves.
- Wear suitable protective goggles.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- Protect your hands with waterproof, robust gloves.
- Wear long trousers.
- Avoid longer skin contact.
- In case of contact with skin, rinse immediately with plenty of water.
- The longer fresh adhesive or laying materials remain on skin, the greater the risk of serious skin damage.

- Keep away children from fresh adhesive and laying material.

The applicable recommendations, guidelines, DIN regulations and safety data sheets are to be observed, together with the recognised architectural and engineering regulations. We guarantee that our products leave the factory in perfect condition. While our recommendations for use are based on tests and practical experience, they can only provide general guidance without any assurance as to product characteristics, since we have no influence over the conditions on site, the execution of the work or the method of processing. This product data sheet supersedes all previous editions.



The Sika management system is certified to ISO 9001 and 14001 by SQS

Sika Deutschland GmbH

Subsidiary Rosendahl

P.O. Box 11 40

D-48713 Rosendahl / Germany

Phone +49 (0) 2547-910-0

Fax +49 (0) 2547-910-101

E-mail: info@schoenox.de

www.schoenox.com